



FS RUZAFa/22,3X22,3X0,9

Model: **FS RUZAFa/22,3X22,3X0,9**
Reference: **40469** **MIX**
Size: **22,3x22,3** cm
Thickness: **9,00** mm
Finish: **Natural**
Body Type: **PORCELAIN - GROUP Bib**
GL - GLAZED Ceramic Tile

Water absorption

EN ISO-10545-3	Water absorption	0,5% < E < 3%
----------------	------------------	----------------------------

Dimensional characteristics

EN ISO-10545-2	Surface quality	> 95%
EN ISO-10545-2	Curvature flatness	± 0,5 % / ± 2,0 mm
EN ISO-10545-2	Thickness	± 5% / ± 0,5 mm
EN ISO-10545-2	Length and Width	± 0,6 % / ± 2,0 mm
EN ISO-10545-2	Rectangularity	± 0,5% / ± 2,0 mm
EN ISO-10545-2	Straightness of sides	± 0,5 % / ± 1,5 mm

Mechanical characteristics

EN ISO 10545-11	Crazing resistance	Pass
EN ISO 10545-12	Frost resistance	Pass
EN ISO 10545-9	Thermal shock resistance	Pass
EN ISO-10545-4	Breaking strength	> 1100 N
EN ISO-10545-4	Modulus of rupture	> 30 N/mm²

Surface characteristics

EN ISO 10545-7	Surface abrasion resistance	4
EN ISO 10545-7	Visible failure at No of revolutions	6000 rev.
EN-101	Surface scratch resistance	5

Chemical characteristics

EN ISO-10545-13	High concentrations of acids and alkalis	HA/HA/HA
EN ISO-10545-13	Low concentrations of acids and alkalis	LA/LA/LA
EN ISO-10545-13	Household chemicals and swimming pool salts	A/A



FS RUZAFa/22,3X22,3X0,9

Model: **FS RUZAFa/22,3X22,3X0,9**
 Reference: **40469** **MIX**
 Size: **22,3x22,3** cm
 Thickness: **9,00** mm
 Finish: **Natural**
 Body Type: **PORCELAIN - GROUP B1b**
GL - GLAZED Ceramic Tile

Chemical characteristics

EN ISO-10545-14	Stain resistance	5/-/5/5
-----------------	------------------	---------

Non-slip characteristics

ANSI A137	Dynamic coefficient of friction (DCOF)	> 0,42
BS-7976-2	Slip resistance test (PTV) - wet conditions	+36
DIN-51130	Critical angle (footwear)	R-10
UNE-41901:2017 EX	Slip resistance (pendulum test)	2

CE MARKING



CE Declaration of Performance: **002CPR2017-08-01**

% RECYLED CONTENT



ISO 14021: Labels and Declarations - Environmental Claims **51,00 %**

Before laying the tiles, check the shade, calibre and quality. No claims will be accepted once the tiles have been laid. Leave a tile joint of at least 0.5 mm in the case of rectified tiles and 1.5 mm for non-rectified ones. The tile colour shown on this data sheet is merely indicative and it might differ from the real tile colour. This document is purely for sales purposes and it cannot be used in any legal or administrative proceedings, in a witness statement, or as documentary proof without the express permission Francisco Segarra.



FS RUZAF/A/22,3X22,3X0,9

Collection: FS VALENTIA

Reference: 40469

Format: 22,3x22,3 cm

Finish: Natural

Thickness: 9 mm

Technical characteristics

- **Critical angle:** R-10
- **Pendulum test:** 2
- **British pendulum test:** 36
- **Coefficient of friction:** > 0,42
- **Hardness standard:** 5

Packaging details of box

Tiles per box: 13

Metres per box: 0.65 m

Weight per tile: 0.952 kg

Weight per box: 12.576 kg

Packaging details of pallet

Pallet: T

Dimensions: 120x80,00 cm

Boxes: 90

Stacked levels: 3

Weight (kg): 0.952

Price group: BN-169

Tile body: Porcelain tile

Sale by tiles or m2: M2